



820P

B1 FIRE RATE PU GUN FOAM

Akfix 820P, is a single component, moisture curing, self-expanding, ready to use polyurethane foam with propellants which are completely harmless to ozone layer. It has a fire resistance up to 235 minutes, recommended for sealing applications where fire resistance is required.

FEATURES & BENEFITS

- According to EN 1366-4 fire resistance up to 235 min
- Efficient seal against smoke and gas.
- Gun use, reusability and precise application.
- Does not contain CFC's and H-CFC's.
- Excellent adhesion & filling capacity.
- Excellent mounting capacity and stability.
- High yield up to 55 liters depending on temperature and humidity.
- High thermal & acoustical insulation value.
- After cured, it can be painted, cut, trimmed.
- Mould and water resistant.
- Conforms to fire class B1 (DIN 4102).

APPLICATIONS

All applications where fire retardant properties are required such as:

- Installation of door and window frames.
- Filling and sealing gaps, joints and cavities.
- Filling of penetrations in walls.
- Heat insulation of roof construction.
- Sealing of cable and pipe penetrations.
- Bonding of insulation materials.
- Multi-Purpose, adhesion and fixation.

INSTRUCTIONS

- Application surface must be free from dust and grease.
- During the application, the temperature of the can and the room temperature should be between +5 °C and +30 °C.
- To get the best result, the temperature of the can and the room temperature should be between +20°C and +25 °C.
- Shake the can well before screwing the adapter on to applicator gun.
- The output of the foam can be regulated with the trigger and controlled with the adjustment screw on the back side of the gun.
- Fill holes and cavities accordingly as the foam will expand around 30% depending on the humidity.
- Moistening the surfaces before and after the application ensures faster curing and increase the bonding strength.
- Fresh foam can be removed using Akfix 800C Foam Cleaner. Cured foam can only be removed mechanically.



Fire Resistant
Gap Filling
& Insulation



STANDARDS

Meets or exceeds the requirements of the following specifications:

- Tested according to EN 1366-4 fire resistance of linear joints in various joint combinations.
- The French VOC requirements for class A+
- The requirements of VOC content specifications in LEED credit EQc4.1 “Low-emitting products” of SCAQMD rule 1168.

RESTRICTIONS

- Storage above +25 °C and below +5 °C shortens shelf life.
- Should be stored and transported in vertical position.
- Should be kept in room temperature for at least 12 hours before the application.
- Cured foam will discolor if exposed to ultraviolet light.
- Paint or coat the cured foam for best results in outdoor applications.

SAFETY

- Contains Diphenylmethane-4, 4'-Diisocyanate.
- Harmful by inhalation. Irritating to eyes, respiratory system and skin. Do not breathe spray/vapour.
- Wear suitable protective clothing and gloves. Use only in well-ventilated areas.
- Pressurized container. Keep away from direct sunlight and do not expose temperatures over 50 °C.
- Do not pierce or burn, even after use.
- Keep away from sources of ignition, no smoking.
- Keep out of the reach of children.

STORAGE AND SHELF LIFE

- 9 months if stored properly.

PROPERTIES

Basis	: Polyurethane Prepolymer	
Curing System	: Moisture cure	
Specific Gravity	: 22±3 Kg/cm ³	(ASTM D1622)
Tack-Free Time (1 cm width)	: 7±3 min	(ASTM C1620)
Cutting Time (1cm width)	: 30-45 min	(ASTM C1620)
Cure-Time	: 24 hours	
Foam Colour	: Red	
Yield	: 30-45 L	(ASTM C1536)
Post Expansion	: 200-250 %	
Shrinkage	: 0 %	
Fire Class of the Cured Foam	: B1	(DIN 4102)
Thermal Conductivity	: 0,036 W/m.k (at 20°C)	(DIN 52612)
Compression Strength	: 0,03 MPa	(DIN 53421)
Water Absorption	: Max. 1 vol%	(DIN 53428)
Temperature Resistance	: -40°C to +90°C	
Application Temperature	: +5°C to +30°C	
Can temperature	: +5°C to +30°C	

The results were obtained by providing optimum environmental conditions.



Test Results –Yıldız Technical University; EN 1366-4

Wall Thickness	Joint Dimension	Backing Material	Fire Resistance in minutes
200mm	Width: 11 mm Depth: 200 mm	None	235 min. Fire rating EI 180
200mm	Width: 41 mm Depth: 200 mm	None	114 min. Fire rating EI 90
100mm	Width: 31 mm Depth: 100 mm	None	52 min. Fire rating EI 45
100mm	Width: 11 mm Depth: 100 mm	None	106 min. Fire rating EI 90

Test Results –Efectis ERA Global; EN 1366-4

Wall Thickness	Joint Dimension	Backing Material	Fire Resistance in minutes
200mm	Width: 11 mm Depth: 200 mm	None	217min. Fire rating EI 180
200mm	Width: 31 mm Depth: 200 mm	None	147 min. Fire rating EI 120
100mm	Width: 21 mm Depth: 100 mm	None	64 min. Fire rating EI 60
100mm	Width: 11 mm Depth: 100 mm	None	80 min. Fire rating EI 60

PACKAGING

Product	Weight	Package
820P	1000gr.	12

DISCLAIMER

The technical data contained herein is based on our present knowledge and experience and we cannot be held liable for any errors, inaccuracies, omissions or editorial failings that result from technological changes or research between the date of issue of this document and the date the product is acquired. Before using the product, the user should carry out any necessary tests in order to ensure that the product is suitable for the intended application. Moreover, all users should contact the seller or the manufacturer of the product for additional technical information concerning its use if they think that the information in their possession needs to be clarified in any way, whether for normal use or a specific application of our product. Our guarantee applies within the context of the statutory regulations and provisions in force, current professional standards and in accordance with the stipulations set out in our general sales conditions. The information detailed in the present technical data sheet is given by way of indication and is not exhaustive. The same applies to any information provided verbally by telephone to any prospective or existing customer.